## Dry lining to walls with chemical dpcs

(Withdrawn - January 2024)

The Technical Guidance Notes are produced by NHBC as guidance solely for our builder customers as to how to interpret the technical requirements in relation to the warranty cover provided by NHBC under its Buildmark, Buildmark Choice, Buildmark Link, Buildmark Solo, Buildmark Connect or any similar product from time to time. It has not been created or intended for distribution or use outside of that purpose. The information contained in this Technical Guidance Note does not constitute advice and is not to be relied upon by any third party. Nothing in this Technical Guidance Note is intended to, nor should it be taken to, create any legal or contractual relationship. Any third party who chooses to rely upon the information contained in the Technical Guidance Notes shall do so entirely at their own risk and NHBC accepts no duty of care or liability, however caused, in connection with its use or reliance by any third party.

## Question

Can dry lining be fixed using adhesive dabs to walls that have received a chemical injected damp proof course?

## Considerations

- Plasterboard manufacturers recommend that adhesive dabs should not be used if the background may be damp.
- Walls that have received a chemical injected damp proof course may take a considerable time to dry to an
  acceptable moisture content.
- Contamination on the surface of the wall such as salts may affect the bond of the adhesive to the wall.
- Hydroscopic salts in the wall may attract moisture that can break down the adhesive.

## **Answer**

Dry lining should not be fixed using adhesive where the walls have previously suffered dampness.

Dry lining should instead, be fixed to treated timber, or metal firrings. These should be mechanically fixed to the wall over strips of vertical dpc.



NHBC, NHBC House, Davy Avenue, Knowlhill, Milton Keynes, Bucks MK5 8FP Tel: 0344 633 1000 Web: nhbc.co.uk